

| | |
|---|---|
| <p>99-071621/07 D25 HENK 97.06.25 HENKEL KGAA *DE 19727073-A1 97.06.25 97DE-1027073 (99.01.07) C11D 17/00, 1/83 Coated active particles for detergents, set free at appropriate temperature - obtained by dispersing particles with melt of coating material and granulating at below melting range C99-021468 Addnl. Data: GASSENMEIER T, MILLHOFF J</p> | <p>D(11-D1A, 11-D1B, 11-D3)</p> |
| <p>Production of coated solid particles comprises cooling a dispersion of particles in a melt of a room-temperature solid, water-insoluble coating material and then granulating at a temperature within the plastic solidifying range of the melt, the particles having a minimum size of at least 0.05 (especially at least 0.1) mm.</p> <p>The coated particles are claimed <i>per se</i>.</p> <p><u>USE</u> The particles are used in cleaning agents e.g. detergents, especially in cleaning hard surfaces, i.e. in dishwasher machines or in washing-up liquids (claimed).</p> | <p><u>ADVANTAGE</u> The particles are rapidly and completely set free from the coating when the temperature exceeds the lower limit of the melting range. Less than 30 wt.% is set free in water at temperatures after 10 minutes at within 6 °C below the lower melting limit.</p> <p><u>PREFERRED PARTICLES</u> The coating has a melting range of 45-75 °C and is especially a paraffin with melting point 50-55°C, while the particles are in crystalline form and are enzymes, bleaching agents, bleach activators, surfactants or perfumes, especially N, N, N',N'-tetraacetylenediamine (TAED). Granulation is followed by sieving with a mesh of no more than 2 mm.</p> <p><u>EXAMPLE</u> A product showing only a small amount of actives set free below the melting range within 10 minutes but as much as 80% dissolving in a detergent solution after 1 minute at a temperature above the melting</p> |

DE 19727073-A+

| | |
|---|----------------------|
| <p>range was obtained by contacting at 55 °C 1 part TAED of average crystallite diameter 0.1 mm with 1 part paraffin (m.pt. 51-53 °C) and then granulating at 48 °C with a 1 mm mesh. (LB) (12pp1958DwgNo.0/3)</p> | <p>DE 19727073-A</p> |
|---|----------------------|